



► Water Rub

—TEST NO. TP07—

I. Scope

This test procedure is used to determine the water resistance of the paint/polymer system, used in the Texture Panels system.

II. Materials and Equipment

- a. Tap water.
- b. Texture Panels production coated parts with barrier coat and top coat.
- c. Kleenex or towel.

III. Procedure

- a. Age finished parts for 1 week at room temperature (77 degrees F)
- b. Immerse part in container with tap water for 5 minutes.
- c. After 5 minute period, pull the part from the container and rub test part with Kleenex or towel firmly. Rub in a 1" back and forth motion. Each back and forth motions counts as one double rub.
- d. Double rub panel 50 times.

IV. Report

- a. Report any loss of coating on surface at number of rubs point.
- b. Compare test results to Texture Panels standard parts.

V. Results

- a. The parts tested passed. There was no loss of coating on the Texture Panels samples tested.

CONTACT